

BOSTON SPATOLATO

Rev.01/2019

DESCRIPTION

Single-component filler paste with a pleasing aesthetic effect. The treated surface is smooth, free from joints or breaks and with a trowel effect that can be more or less pronounced. It has good resistance to wear, chemical agents and footfall. Easy to clean, it is available in customized colours and in GRANA FINE (0.1 mm) and GRANA GROSSA (0.3-0.4 mm).

USES

It is particularly suitable as a finish for walls and floorings in showrooms, shops, homes, hotels, restaurants, offices and in general.

PREPARING THE SURFACE

For best results it is essential to observe the rules for proper cleaning of the surface to be coated. The application surface should be clean and dry.

Tiled surfaces: Sand until the surface has matted to a sufficient grade of porosity. Apply BOSTON PRIMER as an anchor diluted to max 5% water. After drying, level the joints with BOSTUK if sanding is necessary.

Masonry and conglomerates: After seasoning (at least 30 days) remove all traces of dust from the surface and ensure that there is no saltpetre and humidity, also thoroughly eliminate any grease or oil stains. Any previous coverings must be removed and brushed, as well as all the concrete substrate's incongruent parts. For dry compact surfaces, use BOSTON PRIMER diluted with max 5-10% water. For powdery surfaces, prime with BOSTON PRIMER diluted with up to 30-40% water.

To obtain a high degree of surface finishing, apply BOSTON EP AUTOLIVELLANTE as an intermediate coat.

APPLICATION

Apply BOSTON SPATOLATO in millimetres, through the use of a stainless steel spatula for material effects and a plastic spatula for monolithic effects. When the first layer is dry, proceed to further levelling, taking care to eliminate smudges or surface incongruencies. To achieve the desired trowel effects, it may be necessary to repeat the levelling operation 3-4 times. Once the product is hardened, proceed to refining by sanding.

It is important not to execute, in a single solution, applications greater than 3-4 mm as being the product component, the curing process would become longer with consequent formation of withdrawal cracks from refilling. Any amounts in excess of 2/3 mm must be done in stages. Before proceeding with successive coating, ensure that the underlying layer has fully hardened.

Apply with an ambient temperature of between 5C and 35C and humidity inferior to 75%. Do not apply under direct sunlight.

For an excellent and durable finish it is essential to complete any cycle with BOSTON FINITURA.

DILUTION

Ready to use.

TECHNICAL DATA

PRODUCT	Filler paste with aesthetic effect
SPECIFIC WEIGHT	1.400 ± 0.050 kg/l.
VISCOSITY	Thixotropic
GLOSS	Gloss (85 °): 10±1
COLOUR	On request
THICKNESS RECOMMENDED	1-3 mm buckets for single hand
NUMBER OF COATS RECOMMENDED	2-3 hands at a distance of 4-6 hours
RE-COATING	Unlimited
APPLICATION METHOD	Spatula
THEORETICAL YIELD:	0.5-1 Kg/ m ² for 1 layer of 500-600 microns
DRYING TIME (at 23 ° C)	
Tack	30 minutes
Touch dry	4 hours
Deep dry	8 hours

CLEAN TOOLS

With water immediately after use.

STORAGE

Keep away from heat, in a cool and ventilated place, protected from chills.

The above technical knowledge regarding the application and the proper use of the products does not mean ALCAS ITALIA s.r.l. assumption of responsibility for the use and application of the products. Because of the unpredictable variability of operating conditions, the APPLICATOR must verify the use of the product under their own conditions with direct evidence. We reserve the right to change the contents of this document without prior notice. As soon as a new version of this data sheet is available, it will no longer be valid.