

COPRIFUMO

Rev.01/2019

DESCRIPTION

Highly washable smoke-proof paint, recommended for covering smoke stains and yellowed walls. Its high coverage makes it suitable for premises exposed to fumes of various kinds such as: bakeries, patisseries, rooms with fireplaces and kitchens. The functional characteristics such as whiteness and coverage are not obtained to the detriment of the aesthetic aspect, since the product, once applied, has a very pleasant and fine appearance, velvety to the touch and with good opacity characteristics.

USES

It is ideal for ceilings and walls of all environments that are particularly exposed to agents such as smoke, nicotine and pollutants.

PREPARING THE SURFACE

New walls: Fill, sand, dust and impress with CLK diluted in water to 100%. Once the fixative has been cured, apply the ISOLCOPREX INTERIOR pigment base to even out the substrate.

Already treated walls: Remove most of the previous paint or all flaking parts, plaster, sand, dust, and finally apply a coat of primer with CLK diluted in water to 100%. Once the fixative has been cured, apply the ISOLCOPREX INTERIOR pigment base to even out the substrate.

Walls already treated with tempera paint or similar: moisten the surface with water, scrape well and finally proceed as for new walls.

In any case, the surface must be perfectly dry and well-seasoned (at least 4-6 weeks), free from efflorescence, oily and saline residues, from plant formations and bacterial contamination, including any previously repaired areas.

APPLICATION

Apply at least two coats of COPRIFUMO by brush or roller. Allow at least 6 hours from the base coat and at least 8 hours between the first and second coat. Apply between temperatures of 5 and 30 ° C. Do not apply on surfaces that are in direct sunlight, hot or cold, or in the presence of strong wind, if rain is imminent or in the presence of high relative humidity. Stir well before use.

DILUTION

Add 30-35% water.

TECHNICAL DATA

PRODUCT	Super washable smoke-covering paint
SPECIFIC WEIGHT	1.360 ± 0.05 kg/L
VISCOSITY	18000 ± 2000 Brookfield cPs at 23 °C
pH	7-9

GLOSS	opaque <10 G.U. 85°
COVERING CAPACITY	Class 2
WET ABRASION RESISTANCE	Class 2
COLOUR	White
RECOMMENDED THICKNESSES	30÷40 microns per coat
NUMBER OF COATS RECOMMENDED	2 coats
RE-COATING	8-10 hours
APPLICATION METHOD	Brush, roller
THEORETICAL YIELD:	7-9 sqm / l for two layers
DRYING TIME (at 23 ° C)	
Touch dry	Around 2 hours
Deep dry	18-24 hours

CLEAN TOOLS

With water immediately after use.

STORAGE

Keep away from heat, in a cool and ventilated place, protected from chills.

The above technical knowledge regarding the application and the proper use of the products does not mean ALCAS ITALIA s.r.l. assumption of responsibility for the use and application of the products. Because of the unpredictable variability of operating conditions, the APPLICATOR must verify the use of the product under their own conditions with direct evidence. We reserve the right to change the contents of this document without prior notice. As soon as a new version of this data sheet is available, it will no longer be valid.