

TETTO FLASH

Rev.01/2019

DESCRIPTION

Acrylic coating. It has a good resistance to atmospheric agents and to foot traffic, which make it particularly useful for waterproofing surfaces exposed to the elements.

USES

Suitable for the protection and waterproofing of concrete and bituminous surfaces.

PREPARING THE SURFACE

Check that it is completely dry, free of efflorescence and oily residues. Brush and dust the surface to be treated well, removing any remaining flaking residue. In the presence of smooth or non-porous floors, it is necessary to roughen the surface to promote the adhesion and penetration of the paint. After cleaning older liquid and bituminous sheaths, it is always necessary to do an adhesion test prior to the execution of the work.

In any case, but above all with a particularly powdering surface, initially apply a consolidating coat of appropriately diluted SOLVEX primer and wait at least 18 hours before over-coating.

For an optimal result, it is important that the surface's slope ensures proper rainwater flow.

APPLICATION

Apply at least two coats of TETTO FLASH by pure bristle brush, wool roller or spray. Leave at least 8 hours between one coat and the other, taking care to leave a total thickness of about 1 or 1.5 mm. The application temperature must be between 5°C and 35°C. Do not apply if there is an imminent possibility of rain, on days with high humidity, on directly sunlit or frozen surfaces and when strong winds are present. In addition to the primer coat, always apply at least two coats of finishing in order to obtain a compact and homogeneous film. Once completed, it is necessary to protect the treated surface for at least 48 hours from any rainfall.

DILUTION

Add 40-60% water for the first coat, and max 10% of water for the second coat.

TECHNICAL DATA

PRODUCT	Acrylic paint for roofs
SPECIFIC WEIGHT	1.46 ± 0.05 kg/L
VISCOSITY	20000 ± 5000 Brookfield cPs at 23 °C
GLOSS	Very opaque
COLOUR	Red, green, grey
RECOMMENDED THICKNESSES	400-500 microns per dry coat
NUMBER OF COATS RECOMMENDED	2 coats

RE-COATING

APPLICATION METHOD

THEORETICAL YIELD:

DRYING TIME (at 23 ° C)

Touch dry

Deep dry

8-10 hours

Brush, roller or spray

2-3 sqm /l for 2 layers

Around 2 hours

18-24 hours

CLEAN TOOLS

With water immediately after use.

STORAGE

Keep away from heat, in a cool and ventilated place, protected from chills.

The above technical knowledge regarding the application and the proper use of the products does not mean ALCAS ITALIA s.r.l. assumption of responsibility for the use and application of the products. Because of the unpredictable variability of operating conditions, the APPLICATOR must verify the use of the product under their own conditions with direct evidence. We reserve the right to change the contents of this document without prior notice. As soon as a new version of this data sheet is available, it will no longer be valid.