

Alcaquarz

Description

Fine-quartz outdoor paint, formulated with selected binders, sands and mineral fillers which impart high resistance to atmospheric agents. It is characterized by excellent filling power, good breathability and high scrub resistance. With a matt homogeneous appearance, it is ideal for filling substrate flaws and for masking defects. The ALCAQUARZ product complies with the Minimum Environmental Criteria (CAM) established by the Ministerial Decree of 23 June 2022.

Uses

Indicated both for restoring old buildings or for finishing new buildings. Suitable for application on new or old lime-based or cement based top-coat plasters.

Surface preparation

Ensure that the substrate is perfectly dry and seasoned (4-6 weeks), levelled, smooth and finely finished, free from friable and oily residues, saline efflorescences, plant formations, bacterial colonies.

New substrates: brush, dust until all impurities are removed, plaster if necessary, then prime with SOLVEX or CLK appropriately diluted.

Old or chalking substrates, or outdoor : brush, dust until any flaking part is removed, plaster if necessary, then consolidate with primer SOLVEX.

NB In case of particularly chalking surfaces, or treated with plaster, before applying the finish coats wait for complete seasoning (15-30 days in ideal environmental conditions), then prime with SOLVEX appropriately diluted.

Application

Apply at least 2 coats of ALCAQUARZ by brush, roller or spray. Allow at least 18 hours from the primer coat, and at least 8 hours between the 1st and the 2nd coat of paint.

Apply at temperatures between 5°C and 30°C. Do not apply on hot or ice-cold surfaces, nor exposed to sun, in presence of strong wind, in imminence of rain or with high relative humidity. Mix well before use.

Dilution

Add 20-25% of water.

Cleaning tools

With water immediately after use.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinaro (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems

UNI EN ISO 9001:2015

Certified organization



Environmental management
systems

UNI EN ISO 14001:2015

Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, protected from frost.

Technical data

PRODUCT	Quartz outdoor paint
SPECIFIC WEIGHT	1,570 ± 0,050 kg/l
VISCOSITY	45000 ± 1000 cP Brookfield at 23°C
pH	8-9
GLOSS	Matt (<10 g.u. 85°)
COLOUR	White, <i>palette</i> tones
RECOMMENDED THICKNESS	60-70 dry µm for each coat
RECOMMENDED COATS	2 coats
RECOAT TIME	8-10 hours
APPLICATION METHOD	Brush, roller, spray
THEORETICAL YIELD	4-5 m ² /l for 2 coats
TOUCH-DRY (23°C)	1-2 hours
DEEP-DRY (23°C)	18-24 hours

REV 1/2025

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinara (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems
UNI EN ISO 9001:2015

Certified organization



Environmental management
systems
UNI EN ISO 14001:2015