

# Coprifumo

## Description

Anti-Smoke Super Washable Paint, suitable for covering smoke stains and yellowed walls. Its high coverage makes it ideal for areas particularly exposed to various types of smoke, such as: bakeries, pastry shops, rooms with fireplaces, and kitchens. Furthermore, functional characteristics like whiteness and coverage do not compromise aesthetics, as the product, once applied, presents a very pleasing and fine appearance, velvety to the touch and with good opacity.

## Uses

For ceilings and walls of environments particularly exposed to smoke, nicotine and pollutants.

## Surface preparation

**New Walls:** Fill, sand, dust, and prime with FUMOFIX.

**Previously Treated Walls:** Remove as much of the previous paint as possible or any loose or peeling areas, fill, sand, dust, and finally apply a coat of primer with FUMOFIX.

## Application

Apply at least 2 coats of COPRIFUMO by brush or roller. Allow at least 6 hours from the base-coat and at least 8 hours between the 1<sup>st</sup> and the 2<sup>nd</sup> coat of paint. Apply at temperatures between 5°C e 30°C. Do not apply on hot or ice-cold surfaces, nor exposed to sun, in presence of strong wind, in imminence of rain or with high relative humidity. Mix well before use.

## Dilution

Add 30-35% of water.

## Cleaning tools

With water immediately after use.

## Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, protected from frost.

### Alcas Italia srl

head office  
via A. Moro, 29  
81031 Aversa (CE)  
PI 03613710619  
SDI 5RU082D

production plant  
Zona Asi Aversa Nord  
81032 Carinara (CE)  
T +39 081 502 6184  
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management  
systems

UNI EN ISO 9001:2015

Certified organization



Environmental management  
systems

UNI EN ISO 14001:2015

## Technical data

PRODUCT	Stain blocking paint
SPECIFIC WEIGHT	1,360 ± 0,050 kg/l
VISCOSITY	18000 ± 4000 cP Brookfield at 23°C
pH	7-9
GLOSS	Matt (<10 g.u. 85°)
HIDING POWER	Class 2
WET SCRUB RESISTANCE	Class 2
COLOUR	White
RECOMMENDED THICKNESS	30-40 dry µm for each coat
RECOMMENDED COATS	2 coats
RECOAT TIME	8-10 hours
APPLICATION METHOD	Brush, roller
THEORETICAL YIELD	7-9 m <sup>2</sup> /l for 2 coats
TOUCH-DRY (23°C)	ca. 2 hours
DEEP-DRY (23°C)	18-24 hours

### REV 1/2025

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

### Alcas Italia srl

head office  
via A. Moro, 29  
81031 Aversa (CE)  
PI 03613710619  
SDI 5RU082D

production plant  
Zona Asi Aversa Nord  
81032 Carinara (CE)  
T +39 081 502 6184  
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management  
systems  
UNI EN ISO 9001:2015

Certified organization



Environmental management  
systems  
UNI EN ISO 14001:2015