

Lubens Protettivo

Description

Protective transparent indoor/outdoor varnish for wood. Its particular composition confers high resistance to external aggressive agents and excellent levelling to the paint film. Easy to apply, it is non-yellowing and resistant to UV rays.

Available in glossy or satin version.

Uses

It is suitable for painting wood (including in marine environment). It is also indicated for the quality finishing of door/window frames and furniture.

Surface preparation

New wood, or painted with similar products: sand with fine sandpaper and dust off. If necessary, degrease using a cloth soaked with nitro diluent. For higher protection of the wood and better anchoring, pretreat with 1-2 coats of LUBENS IMPREGNANTE (neutral or coloured).

Painted wood: remove existing layers so as to expose the bare wood, then proceed as for new surface. If the substrate is damaged, repair with plaster, wait for it to dry, sandpaper in order to smoothen the grain of the wood and possible flaws and excess of plaster, dust off.

In any case, the substrate must be dry (on the surface and in depth) and seasoned, free from dust, oil and resin residues, from plant formations and rotteness.

Application

Apply 2-3 coats of LUBENS PROTETTIVO by brush, roller or spray. Allow at least 18 hours between each coat. In order to obtain a perfect finish, it is advised to sand with fine-grain sandpaper between coats.

Apply at temperatures between 5°C and 30°C. Avoid application on ice-cold or damp surfaces, or exposed to sun, in presence of strong wind, in imminence of rain or with high relative humidity. If applied indoors, ensure ventilation during the application. Mix well before use.

Dilution

Add max. 5% (by weight) of DILUENTE A. Mix well before use.

Cleaning tools

With DILUENTE A immediately after use.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinara (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems

UNI EN ISO 9001:2015

Certified organization



Environmental management
systems

UNI EN ISO 14001:2015

Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, repaired from frost.

Technical data

PRODUCT	Synthetic varnish
SPECIFIC WEIGHT	0,940 ± 0,010 kg/l
VISCOSITY	250 ± 50 cP Brookfield at 23°C
GLOSS	Glossy = 90 ± 2 g.u. (60°) Satin = 45 ± 2 g.u. (60°)
COLOUR	Neutral
RECOMMENDED THICKNESS	30-35 dry µm for each coat
RECOMMENDED COATS	2 coats
RECOAT TIME	18-24 hours
APPLICATION METHOD	Brush, roller, spray
THEORETICAL YIELD	8-10 m ² /l for 2 coats
TOUCH-DRY (23°C)	2-3 hours
DEEP-DRY (23°C)	24 hours

REV 1/2025

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinara (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems
UNI EN ISO 9001:2015

Certified organization



Environmental management
systems
UNI EN ISO 14001:2015