

# London

## Description

Super-washable emulsion paint based on high-performance vinyl-acrylic binders, characterized by good hiding power, whiteness and resistance to washing.

## Uses

Suitable for decorating interior surfaces, to which it imparts a pleasant matt velvety appearance together with good scrub resistance.

## Surface preparation

New walls: plaster, sandpaper, dust and prime with ALCAFIX appropriately diluted with water.

Treated interior walls: remove existing paint or any flaking part as much as possible, plaster, sandpaper, dust and then prime with ALCAFIX appropriately diluted.

Walls treated with low-quality paint or similar: wet the surface with water, scrape well and then proceed as for new wall.

In any case, the substrate must be perfectly dry and well seasoned, free from saline efflorescences, oily residues, plant formations, bacterial colonies.

## Application

Apply at least 2 coats of LONDON by brush, roller or spray. Allow at least 12 hours from the primer coat, and at least 8 hours between the 1<sup>st</sup> and the 2<sup>nd</sup> coat of paint. Apply at temperatures between 5°C and 30°C. Mix well before use.

## Dilution

Add 30-35% of water.

## Cleaning tools

With water immediately after use.

## Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, protected from frost.

### Alcas Italia srl

head office  
via A. Moro, 29  
81031 Aversa (CE)  
PI 03613710619  
SDI 5RU082D

production plant  
Zona Asi Aversa Nord  
81032 Carinara (CE)  
T +39 081 502 6184  
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management  
systems  
UNI EN ISO 9001:2015

Certified organization



Environmental management  
systems  
UNI EN ISO 14001:2015

## Technical data

PRODUCT	Super-washable indoor emulsion paint
SPECIFIC WEIGHT	1,570 ± 0,050 kg/l
VISCOSITY	26000 ± 4000 cP Brookfield at 23°C
pH	7-9
GLOSS	Matt (<10 g.u. 85°)
HIDING POWER	Class 2
WET SCRUB RESISTANCE	Class 2
COLOUR	White, <i>palette</i> tones
RECOMMENDED THICKNESS	30-40 dry µm for each coat
RECOMMENDED COATS	2 coats
RECOAT TIME	8-10 hours
APPLICATION METHOD	Brush, roller, spray
THEORETICAL YIELD	5-6 m <sup>2</sup> /l for 2 coats
TOUCH-DRY (23°C)	1-2 hours
DEEP-DRY (23°C)	18-24 hours

### REV 2/2023

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

### Alcas Italia srl

head office  
via A. Moro, 29  
81031 Aversa (CE)  
PI 03613710619  
SDI 5RU082D

production plant  
Zona Asi Aversa Nord  
81032 Carinaro (CE)  
T +39 081 502 6184  
info@alcasitalia.it | [www.alcasitalia.it](http://www.alcasitalia.it)

Certified organization



Quality management  
systems  
UNI EN ISO 9001:2015

Certified organization



Environmental management  
systems  
UNI EN ISO 14001:2015