



Tetto Flash

Description

Acrylic coating. It is characterized by good resistance towards atmospheric agents and adequate treading resistance, which make it particularly useful for waterproofing substrates exposed to the weather.

Uses

Indicated for protecting and waterproofing cementitious substrates and bituminous roofings.

Surface preparation

Ensure that the substrate is perfectly dry, free from saline efflorescences and oily residues. Thoroughly brush and dust the surface to be treated, taking care to remove any friable residue. On smooth or non-porous floorings, it is necessary to roughen the surface to promote adhesion and permeation of the paint. On old liquid or bituminous roof coatings, once cleaned it is always necessary to perform preliminary adhesion tests. In any case, and particularly with chalking substrates, it is necessary to consolidate with primer SOLVEX appropriately diluted and wait for at least 18 hours before recoating.

For best results, it is important to ensure that the slope of the substrate allows for proper drainage of rainwater.

Application

Apply at least 2 coats of TETTO FLASH by pure-bristle brush, wool roller or spray, aiming at a total thickness of 1-1,5 mm. Allow at least 8 hours between each coat. Apply at temperatures between 5°C and 35°C. Do not apply in imminence of rain, with high environmental humidity, onto ice-cold substrates or exposed to sun, in presence of strong wind. In addition to the primer coat, always apply at least 2 finishing coats so as to obtain a compact, homogeneous film. Once the paintwork is completed, it is necessary to protect the treated surface from possible rain for at least 48 hours.

Dilution

Add 40-60% of water for the 1st coat; max. 10% of water for the 2nd coat.

Cleaning tools

With water immediately after use.



systems UNI EN ISO 14001:2015

color your life





Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, protected from frost.

Technical data

PRODUCT Acrylic roof coating SPECIFIC WEIGHT 1,460 ± 0,050 kg/l VISCOSITY 20000 ± 5000 cP Brookfield at 23°C GLOSS Matt COLOUR White, red, green, grey RECOMMENDED THICKNESS 400-500 dry µm for each coat RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) 18-24 hours	i echnicai data	
VISCOSITY 20000 ± 5000 cP Brookfield at 23°C Matt COLOUR RECOMMENDED THICKNESS 400-500 dry μm for each coat RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C)	PRODUCT	Acrylic roof coating
GLOSS Matt COLOUR White, red, green, grey RECOMMENDED THICKNESS 400-500 dry μm for each coat RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	SPECIFIC WEIGHT	1,460 ± 0,050 kg/l
COLOUR White, red, green, grey RECOMMENDED THICKNESS 400-500 dry µm for each coat RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	VISCOSITY	20000 ± 5000 cP Brookfield at 23°C
RECOMMENDED THICKNESS 400-500 dry µm for each coat RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	GLOSS	Matt
RECOMMENDED COATS 2 coats APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	COLOUR	White, red, green, grey
APPLICATION METHOD Brush, roller, spray THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	RECOMMENDED THICKNESS	400-500 dry μm for each coat
THEORETICAL YIELD 2-3 m²/l for 2 coats TOUCH-DRY (23°C) ca. 2 hours	RECOMMENDED COATS	2 coats
TOUCH-DRY (23°C) ca. 2 hours	APPLICATION METHOD	Brush, roller, spray
	THEORETICAL YIELD	2-3 m ² /l for 2 coats
DEEP-DRY (23°C) 18-24 hours	TOUCH-DRY (23°C)	ca. 2 hours
	DEEP-DRY (23°C)	18-24 hours

REV 1/2023

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

Alcas Italia srl

head office via A. Moro, 29 PI 03613710619 SDI 5RUO82D

production plant Zona Asi Aversa Nord 81031 Aversa (CE) 81032 Carinaro (CE) T+39 081 502 6184 info@alcasitalia.it | www.alcasitalia.it Certified organization



Quality management systems UNI EN ISO 9001:2015 Certified organization



Environmental management systems UNI EN ISO 14001:2015