

Tres-Bien

Description

Super-washable matt emulsion paint characterized by excellent whiteness, high hiding power and good resistance to repeated cleaning.

Uses

Suitable for decorating indoor surfaces requiring a pleasant aesthetical finish together with good scrub resistance.

Surface preparation

New walls: plaster, sandpaper, dust and prime with ALCAFIX appropriately diluted with water.

Treated interior walls: remove existing paints and loose parts as much as possible, plaster, sandpaper, dust, then prime with ALCAFIX appropriately diluted.

Walls treated with low-quality paint or similar: wet the surface with water, scrape well, then proceed as for new wall.

In any case, the substrate must be perfectly dry and seasoned, free from saline efflorescences, oily residues, plant formations, bacterial colonies.

Application

Apply at least 2 coats of TRES-BIEN by brush, roller or spray. Allow at least 12 hours from the primer coat and at least 8 hours between the 1st and the 2nd finish coat. Apply at temperatures between 5°C and 30°C. Stir thoroughly before use.

Dilution

Add 20-30% of water.

Cleaning tools

With water immediately after use.

Storage

24 months in sealed container, away from sources of heat, in a cool and ventilated place, protected from frost.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinaro (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems
UNI EN ISO 9001:2015

Certified organization



Environmental management
systems
UNI EN ISO 14001:2015

Technical data

| | |
|-----------------------|--------------------------------------|
| PRODUCT | Super-washable indoor emulsion paint |
| SPECIFIC WEIGHT | 1,540 ± 0,050 kg/l |
| VISCOSITY | 18000 ± 4000 cP Brookfield at 23°C |
| pH | 7-9 |
| GLOSS | Matt (<10 g.u. 85°) |
| HIDING POWER | Class 2 |
| WET SCRUB RESISTANCE | Class 2 |
| COLOUR | White |
| RECOMMENDED THICKNESS | 30-40 dry µm for each coat |
| RECOMMENDED COATS | 2 coats |
| RECOAT TIME | 8-10 hours |
| APPLICATION METHOD | Brush, roller, spray |
| THEORETICAL YIELD | 5-6 m ² /l for 2 coats |
| TOUCH-DRY (23°C) | 1-2 hours |
| DEEP-DRY (23°C) | 18-24 hours |

REV 2/2023

The aforementioned technical notions regarding the application and correct use of the product do not imply liability of Alcas Italia S.r.l. for use and application of the products themselves. Due to the unpredictable variability of application conditions, the USER must verify with direct tests the suitability of the product for each peculiar use. We reserve the right to modify the content of this document, without notification. As soon as a new version of these technical data sheet becomes available, this one won't be valid any longer.

Alcas Italia srl

head office
via A. Moro, 29
81031 Aversa (CE)
PI 03613710619
SDI 5RU082D

production plant
Zona Asi Aversa Nord
81032 Carinaro (CE)
T +39 081 502 6184
info@alcasitalia.it | www.alcasitalia.it

Certified organization



Quality management
systems
UNI EN ISO 9001:2015

Certified organization



Environmental management
systems
UNI EN ISO 14001:2015